



## Coronavirus Disease 2019 (COVID-19)

# Decontamination and Reuse of Filtering Facepiece Respirators

### Related Pages

[N95 Respirator Summary](#)

[Stockpiled N95 Respirators](#)

Decontamination & Reuse of Filtering Facepiece Respirators

### Summary of updates as of April 22, 2020:

Minor revisions to wording for clarity. Such edits include word changes to: individual facilities using their discretion when determining what decontamination methods to use; Emergency Use Authorization statements; bleach decontamination, and ethylene oxide.

While disposable filtering facepiece respirators (FFRs), like N95s, are not approved for routine decontamination as standard of care, FFR decontamination and reuse may be needed during times of shortage to ensure continued availability. Based on the limited research available, as of April 2020, ultraviolet germicidal irradiation, vaporous hydrogen peroxide, and moist heat have shown the most promise as potential methods to decontaminate FFRs. This webpage summarizes research about decontamination of FFRs before reuse. How (including when) a facility decides to implement specific crisis strategies is at the discretion of its administrators and should be based on present and projected risk mitigation needs and local, regional, and national availability of N95s.

## Introduction

Reusing disposable filtering facepiece respirators (FFRs) has been suggested as a crisis capacity strategy to conserve available supplies for healthcare environments during a pandemic. Strategies for FFR extended use and reuse (without decontamination of the respirator) are currently available from [CDC's National Institute for Occupational Safety and Health \(NIOSH\)](#).

The surfaces of an FFR may become contaminated while filtering the inhalation air of the wearer during exposures to pathogen-laden aerosols. The pathogens on the filter materials of the FFR may be transferred to the wearer upon contact with the FFR during activities such as adjusting the FFR, improper doffing of the FFR, or when performing a user-seal check when redoffing a previously worn FFR. A study evaluating the persistence of SARS-CoV-2 (the virus that causes COVID-19) on plastic, stainless steel, and cardboard surfaces showed that the virus is able to survive for up to 72-hours [1]. One strategy to mitigate the contact transfer of pathogens from the FFR to the wearer during reuse is to issue five respirators to each healthcare worker who may care for patients with suspected or confirmed COVID-19. The healthcare worker will wear one respirator each day and store it in a breathable paper bag at the end of each shift. The order of FFR use should

be repeated with a minimum of five days between each FFR use. This will result in each worker requiring a minimum of five FFRs, providing that they put on, take off, care for them, and store them properly each day. Healthcare workers should treat the FFRs as though they are still contaminated and follow the precautions outlined in our reuse recommendations. If supplies are even more constrained and five respirators are not available for each worker who needs them, FFR decontamination may be necessary.

When information from the manufacturer or a third-party is available showing that respirators can be successfully decontaminated without impacting respirator performance, then FFRs decontaminated following those recommendations can be worn for any patient care activities.

In the absence of guidance or when information is available that a respirator cannot be decontaminated without negatively impacting the performance, respirators may still be decontaminated. However, given the uncertainties on the impact of decontamination on respirator performance, these FFRs should not be worn by HCPs when performing or present for an aerosol-generating procedure.

No current data exists supporting the effectiveness of these decontamination methods specifically against SARS-CoV-2 on an FFR. Other pathogens may also be present on FFRs and there is only limited data available for other pathogens. Further work is needed to assure SARS-CoV-2 and other pathogens are inactivated. Therefore, even after decontamination, these FFRs should be handled carefully.

HCPs should take the following precautionary measures prior to using a decontaminated FFR:

- Clean hands with soap and water or an alcohol-based hand sanitizer before and after touching or adjusting the FFR.
- Avoid touching the inside of the FFR.
- Use a pair of clean (non-sterile) gloves when donning and performing a user seal check.
- Visually inspect the FFR to determine if its integrity has been compromised.
- Check that components such as the straps, nose bridge, and nose foam material did not degrade, which can affect the quality of the fit, and seal.
- If the integrity of any part of the FFR is compromised, or if a successful [user seal check](#) cannot be performed, discard the FFR and try another FFR.
- Users should perform a [user seal check](#) immediately after they don each FFR and should not use an FFR on which they cannot perform a successful user seal check.

Table 1 provides a summary of the crisis standards of care decontamination recommendations.

**Table 1. Summary of crisis standards of care decontamination recommendations**

Method	Manufacturer or third-party guidance or procedures available	Recommendation for use after decontamination	Additional use considerations
Ultraviolet germicidal irradiation (UVGI)	Yes	Can be worn for any patient care activities	<ul style="list-style-type: none"> <li>• Clean hands with soap and water or an alcohol-based hand sanitizer before and after touching or adjusting the FFR.</li> <li>• Avoid touching the inside of the FFR.</li> <li>• Use a pair of clean (non-sterile) gloves when donning and performing a user seal check.</li> </ul>
Vaporous hydrogen peroxide (VHP)			

Method	Manufacturer or third-party guidance or procedures available	Recommendation for use after decontamination	Additional use considerations
Moist heat			<ul style="list-style-type: none"> <li>• Visually inspect the FFR to determine if its integrity has been compromised.</li> <li>• Check that components such as the straps, nose bridge, and nose foam material did not degrade, which can affect the quality of the fit, and seal.</li> <li>• If the integrity of any part of the FFR is compromised, or if a successful <a href="#">user seal check</a> cannot be performed, discard the FFR and try another FFR.</li> <li>• Users should perform a <a href="#">user seal check</a> immediately after they don each FFR and should not use an FFR on which they cannot perform a successful user seal check.</li> </ul>
Ultraviolet germicidal irradiation (UVGI)	No	Can be worn for patient care activities except when performing or present for an aerosol generating procedure	
Vaporous hydrogen peroxide (VHP)			
Moist heat			

Table 2 provides a summary of the decontamination methods evaluated in the referenced literature and the reported effect of each method on FFR performance.

**Table 2. Summary of the decontamination method and effect on FFR performance**

Method	Treatment level	FFR filtration performance	FFR fit performance	Other observations	References
Vaporous hydrogen peroxide (VHP)	<p><b>Battelle report:</b> Bioquell Clarus C HPV generator: The HPV cycle included a 10 min conditioning phase, 20 min gassing phase at 2 g/min, 150 min dwell phase at 0.5 g/min, and 300 min of aeration.</p> <p><b>Bergman et. al.:</b> Room Bio-Decontamination Service (RBDS™, BIOQUELL UK Ltd, Andover, UK), which utilizes four portable modules: the Clarus® R HPV generator (utilizing 30% H<sub>2</sub>O<sub>2</sub>), the Clarus R20 aeration unit, an instrumentation module and a control computer. Room concentration = 8 g/m<sup>3</sup>, 15 min dwell, 125 min total cycle time.</p>	Passed	FFR fit was shown to be unaffected for up to 20 VHP treatments cycles using a head form	Degradation of straps after 30 cycles (Battelle report)	3, 4

Method	Treatment level	FFR filtration performance	FFR fit performance	Other observations	References
Ultraviolet germicidal irradiation (UVGI)	0.5–950 J/cm <sup>2</sup>	Passed	90–100% passing rate after 3 cycles depending on model		2, 3, 7, 8, 9, 10
Microwave generated steam	1100–1250 W microwave models (range: 40 sec to 2 min)	All models passed filtration evaluation for 1 or 20 treatment cycles as per test	95–100% passing rate after 3 and 20 cycles for all models tested		9, 10, 14
Microwave steam bags	1100 W, 90 sec (bags filled with 60 mL tap water)	Passed	Not evaluated		15
Moist heat incubation	15 min–30 min (60°C, 80% RH)	6 of 6 models passed after 3 cycles of contamination	Passed		3, 9, 10
Liquid hydrogen peroxide	1 sec to 30 min (range: 3–6%)	Passed	Not evaluated		3, 7
Ethylene oxide	1 hour at 55°C; conc. range: 725–833/L	Passed	Not evaluated		2, 3, 7

Table 3 provides a summary of the decontamination methods used, the treatment levels assessed, the microbes tested, and the antimicrobial efficacy as reported in the literature.

**Table 3. Summary of decontamination method antimicrobial efficacy**

Method	Treatment level	Microbe tested	Antimicrobial efficacy	References
--------	-----------------	----------------	------------------------	------------

Method	Treatment level	Microbe tested	Antimicrobial efficacy	References
Vaporous hydrogen peroxide (VHP)	<p><b>Battelle report:</b> Bioquell Clarus C HPV generator: The HPV cycle included a 10 min conditioning phase, 20 min gassing phase at 2 g/min, 150 min dwell phase at 0.5 g/min, and 300 min of aeration.</p> <p><b>Bergman et. al.:</b> Room Bio-Decontamination Service (RBDS™, BIOQUELL UK Ltd, Andover, UK), which utilizes four portable modules: the Clarus® R HPV generator (utilizing 30% H<sub>2</sub>O<sub>2</sub>), the Clarus R20 aeration unit, an instrumentation module and a control computer. Room concentration = 8 g/m<sup>3</sup>, 15 min dwell, 125-min total cycle time.</p> <p><b>Kenney personal communication:</b> Bioquell BQ-50 generator: The HPV cycle included a 10 minute conditioning phase, 30–40 min gassing phase at 16 g/min, 25 min dwell phase, and a 150 min aeration phase.</p>	<p><i>Geobacillus stearothermophilus</i> spores</p> <p>T1, T7, and phi-6 bacteriophages</p>	>99.999%	3, 4, 6
Ultraviolet germicidal irradiation (UVGI)	0.5–1.8 J/cm <sup>2</sup>	<p>Influenza A (H1N1)</p> <p>Avian influenza A virus (H5N1),</p> <p>low pathogenic Influenza A (H7N9),</p> <p>A/Anhui/1/2013</p> <p>Influenza A (H7N9),</p> <p>A/Shanghai/1/2013</p> <p>MERS-CoV</p> <p>SARS-CoV</p> <p>H1N1</p> <p>Influenza A/PR/8/34</p> <p>MS2 bacteriophage</p>	99.9% for all tested viruses	12, 13, 14
Microwave generated steam	1100–1250 W microwave models (range: 40 sec to 2 min)	H1N1 influenza A/PR/8/34	99.9%	14
Microwave steam bags	1100 W, 90 sec (bags filled with 60 mL tap water)	MS2 bacteriophage	99.9%	15
Moist heat incubation	15–30 min (60°C, 80% RH)	H1N1 influenza A/PR/8/34	99.99%	14

Method	Treatment level	Microbe tested	Antimicrobial efficacy	References
Liquid hydrogen peroxide	1 sec to 30 min (range: 3–6%)	Not evaluated	Not evaluated	
Ethylene oxide	1 hour at 55°C; conc. range: 725–833 mg/L	Not evaluated	Not evaluated	

## Vaporous hydrogen peroxide, ultraviolet germicidal irradiation, and moist heat are the most promising FFR decontamination methods

Vaporous hydrogen peroxide, ultraviolet germicidal irradiation, and moist heat are the most promising decontamination methods. If FFR decontamination is considered, these methods do not appear to break down filtration or compromise the FFR; however, many of these methods can only be used for limited times.

### Vaporous hydrogen peroxide

Investigations into VHP decontamination of FFRs provides evidence of minimal effect to filtration and fit while demonstrating 99.9999% efficiency in killing bacterial spores. VHP did not reduce the filtration performance of the ten N95 FFR models tested while showing a 6-log reduction in *Geobacillus stearothermophilus* spores [2-4]. In a report prepared by Battelle Memorial Institute, the 3M 1860 FFR was shown to maintain filtration performance for 50 treatment cycles of VHP, also referred to as HPV by some decontamination system manufacturers, using the Clarus® R HPV generator from Bioquell (utilizing 30% H<sub>2</sub>O<sub>2</sub>). Additionally, FFR fit was shown to be unaffected for up to 20 VHP treatments cycles using NPPTL's Static Advanced Headform [4, 5]. Strap degradation occurred after 20 treatment cycles. Kenney et al., co-contaminated 3M 1870 FFRs with three bacteriophages, T1, T7, and Phi 6, and decontaminated the FFRs using VHP generated from the Bioquell's BQ-50 system. The VHP treatment was shown inactivate >99.999% of all phages which was below the limit of detection [6]. Viscusi et al. found that 9 FFR models (three particulate N95, three surgical N95 FFRs and three P100) exposed to one cycle of VHP treatment using the STERRAD 100S H<sub>2</sub>O<sub>2</sub> Gas Plasma Sterilizer (Advanced Sterilization Products, Irvine, CA) had filter aerosol penetration and filter airflow resistance levels similar to untreated models; however, Bergman et al. found that three cycles of VHP treatment using the STERRAD 100S H<sub>2</sub>O<sub>2</sub> Gas Plasma Sterilizer negatively affected filtration performance [2, 3]. Bergman et al. measured acceptable filtration performance for six FFR models (three particulate and three surgical FFRs) that received three cycles of VHP treatment using the Clarus® R HPV generator (utilizing 30% H<sub>2</sub>O<sub>2</sub>) [3]. VHP is a promising method with a potential for high capacity throughput, but certain VHP systems, such as the Clarus® R HPV generator, may be more compatible with FFR decontamination.

### Ultraviolet germicidal irradiation

UVGI is a promising method but the disinfection efficacy is dependent on dose. Not all UV lamps provide the same intensity thus treatment times would have to be adjusted accordingly. Moreover, UVGI is unlikely to kill all the viruses and bacteria on an FFR due to shadow effects produced by the multiple layers of the FFR's construction. Acceptable filtration performance was recorded for eleven FFR models exposed to various UV doses ranging from roughly 0.5–950 J/cm<sup>2</sup> and UVGI was shown to have minimal effect on fit [2, 3, 7, 8, 9, 10]. Heimbuch et al. tested filtration and fit of 15 FFRs and found no adverse effects to FFR performance [11]. Lindsley et al. reported a reduction of the durability of materials of the FFRs for doses ranging from 120–950 J/cm<sup>2</sup>; however, an approximate inactivation of 99.9% of bacteriophage MS2, a non-

enveloped virus, and H1N1 influenza A/PR/8/34 were achieved with much lower doses of approximately 1 J/cm<sup>2</sup> [12–14]. Heimbuch et al. tested the performance of 1 J/cm<sup>2</sup> of UVGI against Influenza A (H1N1), Avian influenza A virus (H5N1), Influenza A (H7N9) A/Anhui/1/2013, Influenza A (H7N9) A/Shanghai/1/2013, MERS-CoV, and SARS-CoV and reported virus inactivation from 99.9% to greater than 99.999% [11]. UVGI is harmful. Proper precautions are required to avoid UVGI exposure to skin or the eyes.

## Moist heat

Moist heat, consisting of 60°C and 80% RH caused minimal degradation in the filtration and fit performance of the tested FFRs [3, 9, 10]. Heimbuch et al. disinfected FFRs contaminated with H1N1 using moist heat, of 65°C and 85% RH, and achieved a minimal of 99.99% reduction in virus [14]. One limitation of the moist heat method is the uncertainty of the disinfection efficacy for various pathogens.

## Steam treatment and liquid hydrogen peroxide are promising methods with some limitations

### Steam treatment

Steam treatment may be a suitable approach for decontaminating FFRs. The limited number of studies for steam report minimal effect on FFR filtration and fit performance and a minimum 99.9% reduction in H1N1 and bacteriophage MS2 [14, 15]. Fisher et al. used microwave steam bags, designed for disinfecting infant feeding equipment, to decontaminate six FFR models and achieved 99.9% inactivation of MS2 bacteriophage. Filtration performance of all tested FFRs scored above NIOSH certification requirements. Three FFRs were further evaluated for three cycles of steam exposure and demonstrated no change in filtration performance [15]. Bergman et al. also demonstrated acceptable filtration performance after three cycles of exposure to microwave generated steam [3]. Microwave generated steam had little effect on FFR fit after exposure to up to three cycles of steam [9, 10]. Using microwaves to produce steam to decontaminate FFRs is not without limitations. Not all microwaves are constructed the same and some are more powerful than others. The effect of higher power microwaves on FFRs is unknown. Furthermore, the metal nosebands of FFRs may cause arcing, sparks inside the microwave oven, during exposure to microwaves.

### Liquid hydrogen peroxide

Liquid hydrogen peroxide showed no effect of FFR filtration performance [3, 7]. Bergman et al. evaluated six FFRs for filtration performance after a 30-minute submersion in 6% hydrogen peroxide. All six FFR models tested demonstrated no changes in filter performance after three cycles of decontamination. FFR fit and disinfection efficacy were not assessed for this method.

Table 4 provides a summary of the decontamination methods evaluated for each FFR model. This table does not serve to confirm that the decontamination method was effective for each FFR model. This table serves to alert the reader about the availability of more information about the decontamination methods for specific FFR models in the literature.

**Table 4. Decontamination methods evaluated for each FFR model**

FFR Model	Type	VHP	UVGI	EtO	Steam	Moist heat	Hydrogen peroxide
3M 1860	N95	x	x	x	x	x	x
3M 1870	N95	x	x	x	x	x	x

FFR Model	Type	VHP	UVGI	EtO	Steam	Moist heat	Hydrogen peroxide
3M 8000	N95	x	x	x	x	x	x
3M 8210	N95	x	x	x	x	x	x
3M 9210	N95		x				
3M Vflex 1805	N95		x				
Alpha protech	N95		x				
Cardinal Health	N95				x		
Gerson 1730	N95		x				
Kimberly Clark PFR-95	N95	x	x	x	x	x	x
Moldex 1512	N95		x				
Moldex 1712	N95		x				
Moldex 2200	N95	x	x	x	x	x	
Moldex 2201	N95	x	x	x	x	x	x
Precept 65-3395	N95		x				
Prestige Ameritech RP88020	N95		x				
Sperian HC-NB095	N95		x				
Sperian HC-NB295	N95		x				
U.S. Safety AD2N95A	N95		x				
U.S. Safety AD4N95A	N95		x				
3M 8293	P100	x	x	x			
Moldex 2360	P100	x	x				
North 8150	P100	x	x				

## Decontamination methods that changed FFR performance or function

Based on the NIOSH-evaluated research, employers should not use the following methods unless data on the safety and



effectiveness of such methods becomes available.

## Autoclave, dry heat, isopropyl alcohol, soap, and dry microwave irradiation

Decontamination using an autoclave, 160°C dry heat, 70% isopropyl alcohol, microwave irradiation and soap and water caused significant filter degradation to both FFRs and particle penetration levels did not meet the levels that NIOSH would allow for approval [2,7].

## Bleach

Viscusi et al. measured the filtration performance of two FFR models submerged into bleach (0.525% sodium hypochlorite and 5.25% sodium hypochlorite) and noted some degradation in filtration performance but not below acceptable levels [7]. Viscusi et al. and Bergman et al. also examined the performance, of 7 FFR and 6 FFR models respectively, submerged in (0.6 % sodium hypochlorite) and found filtration performance was not affected; however residual bleach odors and chlorine off-gassing were noted [2, 3]. Viscusi et al. concluded that bleach decontamination of FFRs should be further evaluated using lower bleach concentration and chemical methods for neutralizing residuals [2].

## Disinfectant wipes

Heimbuch et al. evaluated biological decontamination efficacy and filtration penetration following aerosol exposure of mucin or viable *Staphylococcus aureus* [18]. Following aerosol exposure, respirators were cleaned with three types of wipes: hypochlorite, benzalkonium chloride (BAC), or nonantimicrobial. Particle penetration following cleaning yielded mean values <5%. The highest penetrations were observed in FFRs cleaned with BAC wipes. The BAC wipe caused one sample of FFRs to exceed 5% penetration. Filter penetration following various decontamination methods was shown in this study to vary based on the decontamination method and the model of FFR.

## Since ethylene oxide appeared to be a promising method, it was investigated and found to have a serious limitation.



Ethylene oxide is not recommended as a crisis strategy as it may be harmful to the wearer.


Ethylene oxide (EtO) was shown to not harm filtration performance for the nine tested FFR models [2, 3, 7]. All tests were conducted for one hour at 55 °C with EtO gas concentrations ranging from 725 to 833 g/L. Six models that were exposed to three cycles of 736 mg/L EtO all passed the filtration performance assessment [3]. Data is not available for the effect that EtO treatment may have on FFR fit. However, EtO treatment does not cause visible physical changes to the appearance of FFRs [2, 3]. A serious concern about using EtO for decontamination of large numbers of FFRs is throughput, since relatively long aeration cycles are needed to ensure removal of highly toxic EtO gas [2]. Any use of ethylene oxide (EtO) should be accompanied by studies to ensure no off-gassing into the breathing zone of the wearer as EtO is carcinogenic and teratogenic. Chronic inhalation of EtO has been linked to neurologic dysfunction and may cause other harmful effects to the wearer [16]. EtO should be used in accordance with Occupational Safety and Health Administration standard 29 CFR 1910.1047 [17].

# Other methods for consideration which have not been tested





Hospitals may have other decontamination capabilities on-hand that may be feasible. For example, photodynamic inactivation of pathogens using methylene blue plus visible light exposure is used to treat blood products and there is interest in using the method to decontaminate PPE. There is currently no data to evaluate the effect of this method on FFR filtration and fit [19].

## References

1. van Doremalen, N., et al., *Aerosol and Surface Stability of SARS-CoV-2 as Compared with SARS-CoV-1*. J New England Journal of Medicine, 2020.
2. Viscusi, D.J., et al., *Evaluation of five decontamination methods for filtering facepiece respirators*. Annals of occupational hygiene, 2009. **53**(8): p. 815-827.
3. Bergman, M., et al., *Evaluation of Multiple (3-Cycle) Decontamination Processing for Filtering Facepiece Respirators*. Journal of Engineered Fibers and Fabrics, 2010. **5**(4): p. 33-41.
4. Battelle. *Final Report for the Bioquell Hydrogen Peroxide Vapor (HPV) Decontamination for Reuse of N95 Respirators*. 2016; Available from: <https://www.fda.gov/emergency-preparedness-and-response/mcm-regulatory-science/investigating-decontamination-and-reuse-respirators-public-health-emergencies>  .
5. Bergman, M.S., et al., *Development of an advanced respirator fit-test headform*. Journal of Occupational and Environmental Hygiene, 2014. **11**(2): p. 117-125.
6. Kenney, Patrick, et al. *Hydrogen Peroxide Vapor sterilization of N95 respirators for reuse*. medRxiv (2020).
7. Viscusi, D.J., King, W.P., Shaffer, R.E., *Effect of decontamination on the filtration efficiency of two filtering facepiece respirator models*. Journal of the International Society for Respiratory Protection, 2007. **24**: p. 93-107.
8. Lindsley, W.G., et al., *Effects of ultraviolet germicidal irradiation (UVGI) on N95 respirator filtration performance and structural integrity*. Journal of Occupational and Environmental Hygiene 2015. **12**(8): p. 509-517.
9. Bergman, M., et al., *Impact of Three Cycles of Decontamination Treatments on Filtering Facepiece Respirator Fit*. Journal of the International Society for Respiratory Protection, 2011. **28**(1): p. 48-59.
10. Viscusi, D.J., et al., *Impact of three biological decontamination methods on filtering facepiece respirator fit, odor, comfort, and donning ease*. Journal of Occupational and Environmental Hygiene, 2011. **8**(7): p. 426-36.
11. Heimbuch, B.K. and D. Harnish. *Research to Mitigate a Shortage of Respiratory Protection Devices During Public Health Emergencies*. 2019; Available from: <https://www.ara.com/news/ara-research-mitigate-shortage-respiratory-protection-devices-during-public-health-emergencies>  .
12. Fisher, E.M. and R.E. Shaffer, *A method to determine the available UV-C dose for the decontamination of filtering facepiece respirators*. Journal of Applied Microbiology, 2011. **110**(1): p. 287-295.
13. Mills, D., et al., *Ultraviolet germicidal irradiation of influenza-contaminated N95 filtering facepiece respirators*. American Journal of Infection Control, 2018. **46**(7): p. e49-e55.
14. Heimbuch, B.K., et al., *A pandemic influenza preparedness study: use of energetic methods to decontaminate filtering facepiece respirators contaminated with H1N1 aerosols and droplets*. American Journal of Infection Control, 2011. **39**(1): p. e1-e9.
15. Fisher, E.M., J.L. Williams, and R.E. Shaffer, *Evaluation of microwave steam bags for the decontamination of filtering facepiece respirators*. PLoS One, 2011. **6**(4).
16. Rutala, W.A. and D.J. Weber. *Guideline for disinfection and sterilization in healthcare facilities, 2008*. 2008; Available from: <https://www.cdc.gov/infectioncontrol/guidelines/disinfection/>.
17. Occupational Safety and Health Administration. Ethylene oxide: 29 CFR 1910.1047

18. Heimbuch, B.K., et al., *Cleaning of filtering facepiece respirators contaminated with mucin and Staphylococcus aureus*. American Journal of Infection Control, 2014. **42**(3); p. 265-270.
19. Eickmann, M., et al., *Inactivation of Ebola virus and Middle East respiratory syndrome coronavirus in platelet concentrates and plasma by ultraviolet C light and methylene blue plus visible light, respectively*. Transfusion, 2018. **58**(9): p. 2202-2207.
20. 3M. *Disinfection of Filtering Facepiece Respirators*. Technical Bulletin 2020; Available from: <https://multimedia.3m.com/mws/media/1816576O/disinfection-of-disposable-respirators-technical-bulletin.pdf>. 

## Other resources

- Lowe, J.J. *N95 Filtering Facemask Respirator Ultraviolet Germicidal Irradiation (UVGI) Process for Decontamination and Reuse*. 2020; Available from: <https://www.nebraskamed.com/sites/default/files/documents/covid-19/n-95-decon-process.pdf>   .
- N95DECON [2020]. *A scientific consortium for data-driven study of N95 filtering facepiece respirator decontamination*. Available from: <https://www.n95decon.org/> 
- NIST. *Tool for Evaluation of Vaporized Hydrogen Peroxide Disinfection of N95 Masks in Small Rooms*. Available from: <https://www.nist.gov/services-resources/software/tool-evaluation-vaporized-hydrogen-peroxide-disinfection-n95-masks-small> 

Page last reviewed: April 23, 2020

Content source: National Center for Immunization and Respiratory Diseases (NCIRD), Division of Viral Diseases